

USE

Quick-curing resin for priming slightly damaged concrete floors, floors with small cracks, asphalt, and bituminous membranes.

Broadcast POLYAC® 14 can be used as a quick primer for polyurethane and epoxy floors.

POLYAC® 14 exhibits outstanding adhesion to various substrates and its rapid reaction and high reactivity allow it to be used at temperatures below freezing point.

POLYAC® 14 can be used as concrete protection.

CHEMICAL RESISTANCE

Polymerised POLYAC® resins have high chemical resistance to alkalis, petroleum derivatives, acids, salts and maintenance products. For more information, please contact RESIPLAST NV.

PROPERTIES

- High reactivity
- Short throughput time
- Applicable at low temperatures
- Optimal viscosity
- Wide range of applications
- Optimised polymerisation under adverse conditions
- Apply with roller or brush

APPLICATIONS- PROCESSING

• Preparing the substrate

Concrete must be at least 28 days old, free of curing compound, laitance, grease and oil. Old concrete and mineral substrate must be prepared by shot blasting, sand blasting or pickling.

The maximum moisture content must be less than 4% and the tensile strength of the substrate at least 1.2MPa.

The optimal processing temperature varies between +5°C and +35°C. For temperatures less than +5°C, please contact Resiplast NV.

• Mixing

Mix POLYAC® 14 thoroughly before use. Paraffin may separate during storage.

Dose a quantity of resin that can be processed within a period of 15 minutes. Add 1 to 4% hardener powder. POLYAC® CATALYST has to be ordered separately.

Mix until the powder is completely dissolved.

Temp.:	Grammes of POLYAC® CATALYST per 100 grammes of POLYAC® 14
5°C	4g
10°C	3g
20°C	2g
30°C	1g

• Application

Apply POLYAC® 14 evenly using a rubber squeegee or a short-haired paint roller.

Apply primer until the area is fully covered with a sealing coat.

A second coat of POLYAC® 14 may be required on highly porous substrates.

Do not disturb the paraffin layer that is formed during hardening.

Additional mechanical adhesion can be achieved by broadcasting quartz into the uncured coating. (0.5kg/m²) Polyurethane and epoxy systems can only be applied to broadcast POLYAC® 14 primer.

• Subsequent processing

The cured coating can be covered with other POLYAC® systems after one hour.

As primer on contaminated substrates:

First carry out an adhesion and curing test.

After substrate preparation, take a small quantity of POLYAC® 14. Add 3% POLYAC® CATALYST. Mix until the powder is completely dissolved. Pour a generous layer of the mixture over the surface and allow to harden completely. Test the adhesion by separating the primer from the substrate with a hammer and chisel. In case of a sticky or poorly adhering contact surface, continue to clean the substrate or choose an alternative primer.



PACKAGING

POLYAC® 14	20kg	Metal pail
	180kg	Drum


To be ordered separately

POLYAC® CATALYST	0,5kg	Plastic pail
	5kg	Plastic pail
	25kg	Box

TECHNICAL PROPERTIES RESIN

Appearance:	Low viscosity, colourless, slightly cloudy liquid
Odour:	Methyl methacrylate
Initiator: POLYAC® CATALYST	BPO 50%, as a function of temperature, from 1% to 4% by weight, calculated on percentage of POLYAC® 14
Pot life:	10 to 15min (20°C)
Cleaning of equipment:	MEK or ethyl acetate
Viscosity:	180 - 250MPa.s (20°C Brookfield, spindle III/200 rpm)
Density:	1.0g/cm ³ ±0.2 (20°C)
Flash point:	10°C (MMA, DIN 51755)
Curing test:(test volume)	300g POLYAC®14 with 6g hardener powder
Peak exotherm temperature:	120 – 145°C
POLYAC® 14 + 2% POLYAC® CATALYST	
Density:	0.98kg/dm ³
Colour	Yellow-brown transparent
Shore D hardness	70 – 80

CE CERTIFICATE


Resiplast NV, Gulkenrodestraat 3, B-2160 Wommelgem
12
EN 13813
Synthetic resin based coating for use in buildings.

Reaction to fire	E _{fl}
Release of corrosive substances	SR
Water permeability	NPD
Wear resistance (Taber)	<20mg (CS10-1,000 cycles-1kg)
Adhesive pull strength	B 1.5
Impact resistance (DIN EN ISO 6272)	>8Nm
Sound insulation	NPD
Sound absorption	NPD
Thermal insulation	NPD
Resistance to chemicals	NPD

CONSUMPTION

Consumption: 0.35kg/m²
Consumption is higher for porous substrates.

TO BE PURCHASED SEPARATELY

- Cleaning solvent for tools: MEK solvent
- POLYAC® CATALYST

STORAGE

Store POLYAC® products in a dry, well-ventilated storage area between 5°C and 35°C. Shelf life: 12 months.

When in doubt, contact RESIPLAST NV, stating the batch number on the packaging. Do not discharge into groundwater/surface waters/sewers. Dispose of contaminated packaging and residues in compliance with applicable legal requirements.

SAFETY

Please read the safety data sheets carefully before using POLYAC® products. The products emit a characteristic odour during processing. Provide adequate ventilation. Keep away from sources of ignition. No smoking. Avoid skin contact. Eye irritation and/or hypersensitivity may occur at high vapour concentrations, upon inhalation and/or skin contact. Do not store food or beverages in the work area. Always wear personal protective equipment in accordance with all applicable local regulations and legislation. Gloves and safety goggles are mandatory.

Resiplast 

Steadfast
SPECIALIST PRODUCTS LTD

This information is provided in good faith, but without guarantee. The application, use and processing of the products are beyond our control and therefore entirely your responsibility. Should Resiplast N.V. nevertheless be held liable for any damage, such liability will be limited to the value of the goods delivered by us. We are committed to providing high-quality goods at all times.

This version supersedes all previous versions. Version: 1.3 Date: 23 March 2017 11:10 AM