

WHO-60 Mixing Instructions.

DESCRIPTION: WHO - 60 is a cementitious thixotropic, shrink compensated grout with a specially developed blend of polymeric reinforcing resins.

WHO - 60 is primarily for structural repairs, however, the mixing instructions should be adhered to for similar applications.

MIXING: The WHO - 60 bucket contains approximately 5 kg of powder and approximately 1000 mls of liquid.

1. Empty 3/4 of the liquid into a bucket
2. Add all powder.
3. Using an electric paddle mixer, stir for a minimum of 5 minutes.
4. Add remaining liquid to obtain the correct consistency depending on application.

This will produce a smooth and cohesive grout which can be applied with a finger trowel. Surplus grout on finished surfaces can be allowed to dry and removed with a stiff brush.

POT LIFE: Once mixed the WHO - 60 should be used immediately as application of this product is time sensitive due to rapid curing.

YIELD: The yield for WHO - 60 pack is approximately 3 litres.

STORAGE: Store in cool dry conditions. Shelf life is one year, see batch number for date.

Do not use in temperatures below 5°C